

PRODUCT SPECIFICATION

Quality	GSM	BF	Tear	Factor	COBB (gm/m ²)		Moisture	RCT (knm)	
			MD	CD	Top	Bottom		MD	CD
Tolerance	± 5%	-1	± 5	± 10	± 5	± 5	± 0.5%	± 2	± 2
Korean Kraft Paper 22 BF	180	22	55	80	40	50	6.5/7.0	1.42	0.77
Korean Kraft Paper 22 BF	230	22	65	90	40	50	6.5/7.0	1.80	1.03
Korean Kraft Paper 28 BF	180	28	85	110	40	50	6.5/7.0	2.06	1.42
Korean Kraft Paper 28 BF	230	28	95	120	40	50	6.5/7.0	3.02	1.67

DECKLE

KRAFT MACHINE:

Min: 272 cm

Max: 274 cm

APPLICATIONS

- 1. Making high strength Carton box
- 2. Making wedding cards
- 3. Making tube and cores
- 4. Making edge protector
- 5. Making pallets
- 6. Making Shopping beg

Korean kraft paper made with 100% korean fibre

For more information, please contact your Dev Priya Products Pvt. Ltd representative or visit our website at www.devproduct.com

This information is subject to modification without notification.

